

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/EP05/001537

International filing date: 14 February 2005 (14.02.2005)

Document type: Certified copy of priority document

Document details: Country/Office: EP
Number: 04075463.2
Filing date: 16 February 2004 (16.02.2004)

Date of receipt at the International Bureau: 17 March 2005 (17.03.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

04075463.2

EP/05/1537

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Anmeldung Nr:
Application no.: 04075463.2
Demande no:

Anmeldetag:
Date of filing: 16.02.04
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Stichting Dutch Polymer Institute
Kennispoort
2 John F. Kennedylaan
5612 AB Eindhoven
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Titanocene-based catalyst system

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

C08F4/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT RO SE SI SK TR LI

FE6163

Title**Titanocene-based catalyst system**

The present invention relates to a solid catalyst system comprising a metallocene containing titanium as central metal (titanocene) and a partially dealcoholated adduct of magnesium dihalide and alcohol.

The use of metallocene compounds and, in particular, titanocene compounds as catalyst components for the polymerization of olefins is well known in the art. They are usually used in conjunction with alumoxanes as cocatalysts. The catalyst systems comprising titanocene compounds and alumoxanes can be used supported on an inert support in order to control the morphology of the obtained polymer and to avoid fouling in the reactor, especially in a gas-phase or slurry polymerization processes.

The drawback of the catalyst systems so obtained is that since alumoxanes need to be used in large excess with respect to titanocene compounds the resulting catalyst is very expensive. Therefore it should be desirable to reduce or eliminate the use of alumoxanes. Magnesium chloride is a well-known support for Ziegler-Natta based catalyst systems containing titanium halide. The use of this compound as a carrier for single-site catalysts could be very advantageous, in view of its chemical and structural simplicity, and to the possibility to finely control the porosity of this support and, therefore, to easily tune the porosity of the final catalyst system.

Several catalyst systems trying to solve the problem of the use of alumoxanes in a magnesium halide supported catalyst system have been proposed in the art.

For example in *Macromol. Chem. Phys.* 195, 1369-1379 (1984) $MgCl_2$ in combination with a zirconocene catalyst and trialkylaluminum is used. More recently, in *Macromolecules* 1993, 26, 4712 mixtures of MgR_2 and AlR_2Cl (generating $MgCl_2$ and AlR_3) as cocatalyst components for olefin polymerization using various metallocenes have been used. In various papers, namely, *Korean J. Chem. Eng.* 16(5) 562-570, *Journal of Applied Polymer science* Vol 70, 1707-1715, *Korean J. Chem. Eng.* 19(4) 557-563 and *J. Molec. Catal A* 191, 2003, 155-165 Lee and co-workers, proposed a metallocene-based catalyst system in which alcohol and anhydrous $MgCl_2$ are reacted to form an adduct $MgCl_2$ -alcohol. The adduct, further reacted with trialkylaluminum, is used for

(FE6163-EP)

2

supporting zirconocene compounds. The obtained catalyst system can be used without a further addition of alumoxanes.

In all these documents only metallocene compounds in which the central metal is zirconium have been used, moreover the adduct MgCl_2 alcohol used is not dealcoholated and it is not characterized by particular values of porosity and surface area. As shown in the comparative tests of the present application the use of a dealcoholated adduct of magnesium halide and alcohol improves the activity of the titanium-based catalyst system.

US 5698487 relates to a magnesium halide having a surface area (BET) greater than $50 \text{ m}^2/\text{g}$, porosity (BET) greater than $0.15 \text{ cm}^3/\text{g}$ and porosity (H_g) greater than $0.3 \text{ cm}^3/\text{g}$. The adduct MgCl_2 -alcohol having these features has been used in combination with trialkylaluminum or alumoxane for supporting metallocene compounds. In all the working examples the metallocene compound is combined with trialkylaluminum or alumoxane before contact with the above support. As shown in the comparative test of the present application when the titanocene is not prereacted with trialkylaluminum the polymerization activity of the resulting catalyst system is improved.

The object of the present invention is a catalyst system obtainable by the process comprising the following steps:

a) contacting

- (i) a partially dealcoholated adduct of formula MgT_2wROH wherein T is chlorine, bromine, or iodine, preferably chlorine; R is a linear or branched $\text{C}_1\text{-C}_{10}$ alkyl radical, preferably R is a linear $\text{C}_1\text{-C}_{10}$ alkyl radical; more preferably R is a methyl or an ethyl radical; w ranges from 3 to 0.1, preferably from 3 to 0.5; more preferably from 3 to 1 being also a non integer number; with
- (ii) an organo-aluminium compound of formula $\text{H}_e\text{AlU}_{3-e}$ or $\text{H}_e\text{Al}_2\text{U}_{6-e}$, where the U substituents, same or different, are hydrogen atoms, halogen atoms, or hydrocarbon radicals containing from 1 to 20 carbon atoms optionally containing silicon or germanium atoms; with the proviso that at least one U is different from halogen, and e ranges from 0 to 1, being also a non-integer number; preferably such a hydrocarbon radicals are linear or branched, cyclic or acyclic, $\text{C}_1\text{-C}_{20}$ -alkyl, $\text{C}_2\text{-C}_{20}$ alkenyl, $\text{C}_2\text{-C}_{20}$ alkynyl, $\text{C}_6\text{-C}_{20}$ -aryl,

(FE6163-EP)

C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radicals optionally containing silicon or germanium atoms; preferably U is a linear or branched C_1 - C_{20} -alkyl radical; more preferably U is an ethyl, a n-propyl, a iso propyl, a n-butyl, a iso-butyl, a tert-butyl, a hexyl or an octyl radical; to obtain an adduct of formula (I)



wherein

y ranges from 1.00 to 0.05;

Q has the same meaning of U excluding hydrogen and halogen atoms;

R has been described above

and j ranges from 0.01 to 3.00, being also a non-integer number.

- b) contacting the product obtained from step a) with at least one metallocene compound having titanium as central metal and at least one ligand having a cyclopentadienyl skeleton;

with the proviso that the metallocene compound of step b) is not previously treated with an organo-aluminium compound of formula H_eAlU_{3-e} or $H_eAl_2U_{6-e}$, or with an alumoxane.

In step a) the product obtained by combining the partially dealcoholated adduct of formula MgT_2wROH (i) and organo-aluminium compound of formula H_eAlU_{3-e} or $H_eAl_2U_{6-e}$, (ii) is an adduct of formula (I)




preferably in the compound of formula (I) y ranges from 0.50 to 0.10; more preferably it ranges from 0.40 to 0.10;


j preferably ranges from 2.50 to 2.00; more preferably it ranges from 2.50 to 2.20.

Preferably said adduct of formula (I) has a surface area (BET) higher than $30 \text{ m}^2/\text{g}$; more preferably higher than $38 \text{ m}^2/\text{g}$; even more preferably higher than $200 \text{ m}^2/\text{g}$; but it can reach values higher than $300 \text{ m}^2/\text{g}$.


A preferred class of metallocene compounds to be used in step b) belongs to the following formulas (II), (III), (IV) or (V)




(II)



(III)



(IV)



(V)

wherein

Ti is titanium;

the substituents X, equal to or different from each other, are monoanionic sigma ligands selected from the group consisting of hydrogen, halogen, R^6 , OR^6 , $OCOR^6$, SR^6 , NR^6_2 and PR^6_2 , wherein R^6 is a hydrocarbon radical containing from 1 to 20 carbon atoms optionally containing one or more Si or Ge atoms; preferably R^6 is a linear or branched, cyclic or acyclic, C_1 - C_{20} -alkyl, C_2 - C_{20} alkenyl, C_2 - C_{20} alkynyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl optionally containing one or more Si or Ge atoms; the substituents X are preferably the same and are preferably halogen, R^6 , OR^6 and NR^6_2 ; wherein R^6 is preferably a C_1 - C_7 alkyl, C_6 - C_{14} aryl or C_7 - C_{14} arylalkyl group, optionally containing one or more Si or Ge atoms; more preferably, the substituents X are selected from the group consisting of -Cl, -Br, -Me, -Et, -n-Bu, -sec-Bu, -Ph, -Bz, - CH_3SiMe_3 , -OEt, -OPr, -OBu, -OBz and -NMe₂; more preferably X is Cl or Me.

p is an integer ranging from 1 to 2;

L is a divalent bridging group selected from C_1 - C_{20} alkylidene, C_3 - C_{20} cycloalkylidene, C_6 - C_{20} arylidene, C_7 - C_{20} alkylarylidene, or C_7 - C_{20} arylalkylidene radicals optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements, and silylidene

(FE6163-EP)

5

radical containing up to 5 silicon atoms such as SiMe_2 , SiPh_2 ; preferably L is a divalent group $(\text{ZR}^7_m)_n$; Z being C, Si, Ge, N or P, and the R^7 groups, equal to or different from each other, being hydrogen or hydrocarbon groups containing from 1 to 20 carbon atoms, or two R^7 can form a aliphatic or aromatic C_4 - C_7 ring; preferably R^7 is hydrogen or a linear or branched, cyclic or acyclic, C_1 - C_{20} -alkyl, C_2 - C_{20} alkenyl, C_2 - C_{20} alkynyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radical;

more preferably L is selected from $\text{Si}(\text{CH}_3)_2$, SiPh_2 , SiPhMe , $\text{SiMe}(\text{SiMe}_3)$, CH_2 , $(\text{CH}_2)_2$, $(\text{CH}_2)_3$ or $\text{C}(\text{CH}_3)_2$;

m is 1 or 2, and more specifically it is 1 when Z is N or P, and it is 2 when Z is C, Si or Ge;

n is an integer ranging from 1 to 4; preferably it is 1 or 2;

R^1 , R^2 , R^3 , R^4 and R^5 , equal to or different from each other, are hydrogen atoms, C_1 - C_{40} hydrocarbon groups optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or two adjacent R^1 , R^2 , R^3 , R^4 and R^5 form one or more 3-7 membered ring optional containing heteroatoms belonging to groups 13-17 of the periodic table; such as to form with the cyclopentadienyl moiety the following radicals: indenyl; mono-, di-, tri- and tetra-methyl indenyl; 2-methyl indenyl, 3-butyl-indenyl, 2-isopropyl-4-phenyl indenyl, 2-methyl-4-phenyl indenyl, 2-methyl-4,5 benzo indenyl; 3-trimethylsilyl-indenyl; 4,5,6,7-tetrahydroindenyl; fluorenyl; 5,10-dihydroindeno[1,2-b]indol-10-yl; N-methyl- or N-phenyl-5,10-dihydroindeno [1,2-b]indol-10-yl; 5,6-dihydroindeno[2,1-b]indol-6-yl; N-methyl-or N-phenyl-5,6-dihydroindeno[2,1-b]indol-6-yl; azapentalene-4-yl; thiapentalene-4-yl; azapentalene-6-yl; thiapentalene-6-yl; mono-, di- and tri-methyl-azapentalene-4-yl, 2,5-dimethyl-cyclopenta[1,2-b:4,3-b']-dithiophene;

preferably R^1 , R^2 , R^3 , R^4 and R^5 are hydrogen atoms or linear or branched, cyclic or acyclic, C_1 - C_{40} -alkyl, C_2 - C_{40} alkenyl, C_2 - C_{40} alkynyl, C_6 - C_{40} -aryl, C_7 - C_{40} -alkylaryl or C_7 - C_{40} -arylalkyl radicals, optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or two adjacent R^1 , R^2 , R^3 , R^4 and R^5 form one or more 3-7 membered ring optional containing heteroatoms belonging to groups 13-17 of the periodic table;

A is a NR^8 , O, S radical, wherein R^8 is a C_1 - C_{20} hydrocarbon group optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

(FE6163-EP)

6

preferably R^8 is a linear or branched, cyclic or acyclic, C_1 - C_{20} -alkyl, C_2 - C_{20} alkenyl, C_2 - C_{20} alkynyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl radical optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; more preferably R^8 is tert-butyl.

B is a hydrogen atom, a halogen atom, R^6 , OR^6 , $OCOR^6$, SR^6 , NR^6_2 and PR^6_2 , wherein R^6 has been described above; otherwise B is a NR^9 radical wherein R^9 is a C_1 - C_{40} hydrocarbon group optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

Non limiting examples of compounds belonging to formulas (II), (III), (IV) and (V) are the following compounds (when possible in either their meso or racemic isomers, or mixtures thereof):

bis(cyclopentadienyl)titanium dichloride;

bis(indenyl)titanium dichloride;

bis(tetrahydroindenyl)titanium dichloride;

bis(fluorenyl)titanium dichloride;

(cyclopentadienyl)(indenyl)titanium dichloride;

(cyclopentadienyl)(fluorenyl)titanium dichloride;

(cyclopentadienyl)(tetrahydroindenyl)titanium dichloride;

(fluorenyl)(indenyl)titanium dichloride;

dimethylsilanediylbis(indenyl)titanium dichloride,

dimethylsilanediylbis(2-methyl-4-phenylindenyl)titanium dichloride,

dimethylsilanediylbis(4-naphthylindenyl)titanium dichloride,

dimethylsilanediylbis(2-methylindenyl)titanium dichloride,

dimethylsilanediylbis(2-methyl-4-t-butylindenyl)titanium dichloride,

dimethylsilanediylbis(2-methyl-4-isopropylindenyl)titanium dichloride,

dimethylsilanediylbis(2,4-dichlorideindenyl)titanium dichloride,

dimethylsilanediylbis(2-methyl-4,5-benzoidindenyl)titanium dichloride,

dimethylsilanediylbis(2,4,7-trimethylindenyl)titanium dichloride,

dimethylsilanediylbis(2,4,6-trimethylindenyl)titanium dichloride,

dimethylsilanediylbis(2,5,6-trimethylindenyl)titanium dichloride,

methyl(phenyl)silanediylbis(2-methyl-4,6-diisopropylindenyl)-titanium dichloride,

methyl(phenyl)silanediylbis(2-methyl-4-isopropylindenyl)-titanium dichloride,

(FB6163-EP)

7

1,2-ethylenebis(indenyl)titanium dichloride,
 1,2-ethylenebis(4,7-dichlorideindenyl)titanium dichloride,
 1,2-ethylenebis(2-methyl-4-phenylindenyl)titanium dichloride,
 1,4-butanediylbis(2-methyl-4-phenylindenyl)titanium dichloride,
 1,2-ethylenebis(2-methyl-4,6-diisopropylindenyl)titanium dichloride,
 1,4-butanediylbis(2-methyl-4-isopropylindenyl)titanium dichloride,
 1,4-butanediylbis(2-methyl-4,5-benzoindenyl)titanium dichloride,
 1,2-ethylenebis(2-methyl-4,5-benzoindenyl)titanium dichloride,
 [4-(η^5 -cyclopentadienyl)-4,6,6-trimethyl(η^5 -4,5-tetrahydro-
 pentalene)]dichloridetitanium,
 [4-(η^5 -3'-trimethylsilylcyclopentadienyl)-4,6,6-trimethyl(η^5 -4,5-
 tetrahydropentalene)]dichloridetitanium,
 (tert-butylamido)(tetramethyl- η^5 -cyclopentadienyl)-1,2-ethane-dichloridetitanium,
 (methylamido)(tetramethyl- η^5 -cyclopentadienyl)dichloridesilyl-dichloridetitanium,
 (methylamido)(tetramethyl- η^5 -cyclopentadienyl)-1,2-ethanediyl-dichloridetitanium,
 (tertbutylamido)-(2,4-dichloride-2,4-pentadien-1-yl)dimethylsilyl-dichloridetitanium,
 bis(1,3-dichloridecyclopentadienyl)titanium dichloride,
 methylene(3-methyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b'])
 dithiophene)titanium dichloride;
 methylene(3-isopropyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b'])
 dithiophene)titanium dichloride;
 methylene(2,4-dichloride-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-
 b']) dithiophene)titanium dichloride;
 methylene(2,3,5-trimethyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-
 b:4,3-b']) dithiophene)titanium dichloride;
 methylene-1-(indenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-
 b'])dithiophene)titanium dichloride and dichloride;
 methylene-1-(indenyl)-7-(2,5-ditrimethylsilylcyclopentadienyl-[1,2-b:4,3-
 b'])dithiophene)titanium dichloride;
 methylene-1-(3-isopropyl-indenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-
 b'])dithiophene)titanium dichloride;

(FE6163-EF)

8

methylene-1-(2-methyl-indenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b']dithiophene)titanium dichloride;
methylene-1-(tetrahydroindenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b']dithiophene)titanium dichloride;
methylene(2,4-dimethyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b']dioxazol)titanium dichloride;
methylene(2,3,5-trimethyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b'] dioxazol)titanium dichloride;
methylene-1-(indenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b']dioxazol)titanium dichloride;
isopropylidene(3-methyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b'] dithiophene)titanium dichloride;
isopropylidene(2,4-dimethyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b'] dithiophene)titanium dichloride;
isopropylidene(2,4-diethyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b'] dithiophene)titanium dichloride;
isopropylidene(2,3,5-trimethyl-cyclopentadienyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b'] dithiophene)titanium dichloride;
isopropylidene-1-(indenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b']dithiophene)titanium dichloride;
isopropylidene-1-(2-methyl-indenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b']dithiophene)titanium dichloride;
dimethylsilandiyl-1-(2-methyl-indenyl)-7-(2,5-dimethylcyclopentadienyl-[1,2-b:4,3-b']dithiophene)hafnium dichloride;
dimethylsilanediyl(3-tert-butyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
dimethylsilanediyl(3-isopropyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
dimethylsilanediyl(3-methyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
dimethylsilanediyl(3-ethyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
1-2-ethane(3-tert-butyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
1-2-ethane (3-isopropyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
1-2-ethane (3-methyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
1-2-ethane (3-ethyl-cyclopentadienyl)(9-fluorenyl)titanium dichloride,
(FE6163-EP)

9

dimethylsilandiylbis-6-(3-methylcyclopentadienyl-[1,2-b]-thiophene) dichloride;
dimethylsilandiylbis-6-(4-methylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(4-isopropylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(4-ter-butylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(3-isopropylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(3-phenylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(2,5-methyl-3-phenylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-[2,5-dimethyl-3-(2-methylphenyl)cyclopentadienyl-[1,2-b]-thiophene]titanium dichloride;
dimethylsilandiylbis-6-[2,5-dimethyl-3-(2,4,6-trimethylphenyl)cyclopentadienyl-[1,2-b]-thiophene]titanium dichloride;
dimethylsilandiylbis-6-[2,5-dimethyl-3-mesitylenecyclopentadienyl-[1,2-b]-thiophene]titanium dichloride;
dimethylsilandiylbis-6-(2,4,5-trimethyl-3-phenylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(2,5-diethyl-3-phenylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(2,5-diisopropyl-3-phenylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(2,5-diter-butyl-3-phenylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(2,5-ditrimethylsilyl-3-phenylcyclopentadienyl-[1,2-b]-thiophene)titanium dichloride;
dimethylsilandiylbis-6-(3-methylcyclopentadienyl-[1,2-b]-silole)titanium dichloride;
dimethylsilandiylbis-6-(3-isopropylcyclopentadienyl-[1,2-b]-silole)titanium dichloride;
dimethylsilandiylbis-6-(3-phenylcyclopentadienyl-[1,2-b]-silole)titanium dichloride;

(FE6163-EP)

10

dimethylsilandiylbis-6-(2,5-dichloride-3-phenylcyclopentadienyl-[1,2-b]-silole)titanium dichloride;
dimethylsilandiylbis-6-[2,5-dichloride-3-(2-methylphenyl)cyclopentadienyl-[1,2-b]-silole)titanium dichloride;
dimethylsilandiylbis-6-[2,5-dichloride-3-(2,4,6-trimethylphenyl)cyclopentadienyl-[1,2-b]-silole)titanium dichloride;
dimethylsilandiylbis-6-[2,5-dichloride-3-mesitylenecyclopentadienyl-[1,2-b]-silole)titanium dichloride;
dimethylsilandiylbis-6-(2,4,5-trimethyl-3-phenylcyclopentadienyl-[1,2-b]-silole)titanium dichloride;
[dimethylsilyl(tert-butylamido)][(N-methyl-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(6-methyl-N-methyl-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(6-methoxy-N-methyl-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(N-ethyl-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(N-phenyl-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(6-methyl-N-phenyl-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(6-methoxy-N-phenyl-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(N-methyl-3,4-dichloride-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(N-ethyl-3,4-dichloride-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
[dimethylsilyl(tert-butylamido)][(N-phenyl-3,4-dichloride-1,2-dihydrocyclopenta[2,1-b]indol-2-yl)]titanium dichloride;
as well as the corresponding dimethyl, hydrochloro and dihydro compounds.
(FE6163-EP)

Suitable metallocene complexes belonging to formulas (II), (III) (IV) and (V) are described in WO 98/22486, WO 99/58539 WO 99/24446, USP 5,556,928, WO 96/22995, EP-485822, EP-485820, USP 5,324,800, EP-A-0 129 368, USP 5,145,819, EP-A-0 485 823, WO 01/47939, WO 01/44318, PCT/EP02/13552, EP-A-0 416 815, EP-A-0 420 436, EP-A-0 671 404, EP-A-0 643 066 and WO-A-91/04257.

The partially dealcoholated adduct of formula $MgT_2 \cdot nROH$ used in step a) can be obtained by partial dealcoholation of adducts of MgT_2 with alcohols, said adducts containing from 1 to 6 mol of alcohol. It is possible that two adducts having the same content of alcohol, i.e. having the same brute formula, be different in porosity and surface area for the reason that one adduct is partially dealcoholated.

The dealcoholation can be carried out according to known methodologies such as those described in EP-A-395 083. Depending on the extent of the dealcoholation treatment, partially dealcoholated adducts can be obtained having an alcohol content generally ranging from 0.1 to 3 moles of alcohol per mole of MgT_2 , preferably from 2.9 to 0.5; more preferably from 2.9 to 1.

Said partially dealcoholated magnesium adduct is then contacted with an organo-aluminium compound of formula H_nAlU_{3-n} or $H_nAl_2U_{6-n}$ in an inert solvent with methods common known in the art, such as the method described in EP-A-553 806.

In step b) of the process of the present invention the titanocene compound can be supported on the carrier obtained in step a) according to known methods by bringing the product of step a) into contact, for example, with a solution of the titanocene compound, operating at temperatures between room temperature and 120°C. The metallocene compound that is not fixed on the support is removed by filtration or similar methods or by evaporating the solvent.

The amount of titanocene compound supported on the adduct of formula (I) is generally between 1000 $\mu\text{mol/g}$ of support and 1 $\mu\text{mol/g}$ of support; preferably said amount ranges from 500 $\mu\text{mol/g}$ of support to 2 $\mu\text{mol/g}$ of support; more preferably from 200 $\mu\text{mol/g}$ of support to 2 $\mu\text{mol/g}$ of support.

The catalyst system object of the present invention can be used for (co)polymerizing one or more olefins. Therefore a further object of the present invention is a process for (co)polymerizing olefins containing from 2 to 20 carbon atoms comprising contacting one or more of said olefins under polymerization conditions in the presence of the (FE6163-EP)

12

catalyst system described above. Preferably alpha-olefins containing from 2 to 20 carbon atoms are used.

Examples of alpha-olefins that can be used with the process of the present invention are: ethylene, propylene, 1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene, 1-octene, 4,6-dimethyl-1-heptene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene and 1-eicosene. Preferred olefins are propylene, ethylene 1-butene, 1-hexene and 1-octene.

The following examples are given for illustrative purpose and do not intend to limit the invention.

Materials and general procedures

All manipulations were performed under an argon atmosphere using glove box (Braun MB-150 GI or LM-130) and Schlenk techniques. Solvents were distilled from Na (toluene) or Na/benzophenone (heptane) and freeze-thaw degassed twice before use.

Cp_2TiCl_2 and Cp_2ZrCl_2 were purchased from Aldrich and recrystallised from toluene and dichloromethane respectively prior to use.

rac-Ethylenebis(indenyl)zirconium dichloride ($\text{Et}[\text{Ind}]_2\text{ZrCl}_2$) was prepared according to F.R.W.P. Wild, L. Zsolnai, G. Huttner, H.H. Brintzinger, *J. Organomet. Chem.* **1982**, 232, 233.

$\text{Me}_2\text{Si}(\text{Me}_4\text{Cp})(\text{N}^t\text{Bu})\text{TiCl}_2$ was prepared according to EP 416815.

$\text{Cp}[1,3-(2',6'\text{-Me}_2\text{C}_6\text{H}_3)_2(\text{CH}_2\text{N})_2\text{C}=\text{N}]\text{TiCl}_2$ was prepared according to WO 02/070569.

$(^t\text{Bu}_3\text{P}=\text{N})\text{CpTiCl}_2$ was prepared according to D.W. Stephan, J.C. Stewart, F. Guérin, S. Courtenay, J. Kickham, E. Hollink, C. Beddie, A. Hoskin, T. Graham, P. Wei, R.E.v.H. Spence, W. Xu, L. Koch, X. Gao, D.G. Harrison, *Organometallics*, **2003**, 22, 1937.

CpTiCl_3 was prepared according to A.N. Cardoso, R.J.H. Clark, S. Moorhouse, *J. Chem. Soc., Dalton Trans.* **1980**, 7, 1156.

$(^t\text{BuCp})\text{TiCl}_3$ was prepared according to K. Nomura, N. Naga, M. Miki, K. Yanagi, *Macromolecules*, **1998**, 33, 7588.

$(\text{C}_5\text{H}_4\text{CMe}_2\text{Ph})\text{TiCl}_3$ was prepared according to J. Saßmannshausen, A.K. Powell, C.E. Anson, S. Wocadlo, M. Bochmann, *J. Organometal. Chem.* **1999**, 592, 84.

AlEt_3 (25 wt.% solution in toluene) and AlEt_2Cl (25 wt. % solution in toluene) were obtained from Aldrich, whilst Al^tBu_3 (1M solution in hexane) was purchased from Fluka.

(FE6163-EP)

Ethylene (3.5 grade supplied by Air Liquide) was purified by passing over columns of 4Å Molecular Sieves and BTS copper catalyst.

The Al and transition metal contents were determined by atomic absorption.

Surface area (BET) is determined according to BET methods (apparatus used:

SORPTOMATIC 1800 from Carlo Erba).

The ethoxide content in the magnesium adducts was determined by GC analysis of the ethanol content of a solution obtained by dissolving 100 mg support in 5 mL *n*-BuOH containing a known quantity of *n*-PrOH as internal standard.

Preparation of partially dealcoholated adduct of formula $MgCl_2 \cdot nROH$

The adduct $MgCl_2 \cdot 3EtOH$ was prepared according to the procedure described in Example 2 of Patent U.S. Pat. No. 4,399,054, operating at 3000 rpm instead of at 10000 rpm.

The adduct was partially dealcoholated by heating in a stream of nitrogen at temperatures increasing from 30°C. to 180°C., until an adduct containing the amount of ethyl alcohol reported in table 1 was obtained.

Preparation of the catalyst system, general procedure

step a) preparation of the support $MgCl_2/AlR_3(OEt)_3$

Typically, 10 mL *n*-heptane were added to 1 g of a adduct of magnesium chloride and ethanol prepared according to the procedure reported above under argon and the mixture was cooled to 0 °C. A 25 wt-% solution in the solvent indicated in table 1 of the organo-aluminium compound reported in table 1 was then added gradually, over 5-10 min. in a mol ratio Al/EtOH reported in table 1. The reaction being carried out in a standard Schlenk vessel equipped with a pressure release valve. After standing overnight at room temperature, the mixture was filtered and the solid washed twice with 10 mL heptane.

step b) reaction with the metallocene compound

A solution of the metallocene compound reported in table 2 in toluene (4 mL) was added to 200 mg of support prepared in step a). The mixture was heated to 60 °C and kept at this temperature for 1 h. In the case of Cp_2TiCl_2 , a dark green solid was obtained, the liquid phase having become colorless. The liquid phase was removed by decantation and the solid phase was washed with heptane (2 mL) and dried under a flow of argon at 60°C.

Preparation of the catalyst system, comparative examples I general procedure

step a) preparation of the support $MgCl_2/AlR_n(OEt)_{3-n}$

The same procedure followed for the above step a) was used.

(FE6163-EF)

14

step b) reaction with metallocene compound

A solution of the metallocene compound reported in table 2 (20 μmol) in toluene (4 mL) was mixed with triisobutylaluminum (TIBAL) (100 μmol) to give a violet solution. After 1 h at room temperature, this solution was added to 200 mg of support prepared in step a) as indicated in table 1. The mixture was heated to 60 °C and kept at this temperature for 1 h, after which time a light green solid was obtained. In contrast to the experiments carried out without the catalyst/TIBAL precontact, the liquid phase was not colourless but remained violet. The liquid phase was removed by decantation and the solid phase was washed with heptane (2 mL) and dried under a flow of argon at 60°C.

Preparation of the catalyst system, comparative examples II general procedure**Preparation of non dealcoholated adduct of formula $\text{MgCl}_2 \cdot 2.37\text{EtOH}$**

Following the procedure described by Lee et al. in J. Molec. Catal. A 191, 2003, 155, magnesium chloride (9.52 g) was mixed with ethanol (100 mL) and stirred at 60 °C until dissolved. n-Decane (100 mL) was then added and the mixture stirred at (nominally) 2000 rpm under vacuum at 80 °C. As described by Lee, precipitation was observed as the ethanol evaporated. The solid product was separated by decantation and washed first with toluene (50 mL) and subsequently petroleum ether (40-70 fraction; 2 x 20 mL), then dried under vacuum (1 mbar) for 20 min. to give a fine, free-flowing powder.

Determination of the ethanol content of the product, using a GC method, described above indicated the composition: $\text{MgCl}_2 \cdot 2.37\text{EtOH}$.

step a) preparation of the support $\text{MgCl}_2/\text{AlEt}_n(\text{OEt})_{3-n}$

10 mL n-heptane were added to 1 g of the $\text{MgCl}_2 \cdot 2.37\text{EtOH}$ support obtained as described above under argon and the mixture was cooled to 0 °C. AlEt_3 (25 wt-% solution in toluene) was then added gradually, over 5-10 min., to give a mol ratio $\text{AlEt}_3/\text{EtOH} = 2$, the reaction being carried out in a standard Schlenk vessel equipped with a pressure release valve. The mixture was allowed to warm slowly to room temperature and reaction was continued with occasional agitation for a further 2 days. The resulting support was isolated by filtration, washed with heptane and petroleum ether (40-70) and then dried under a flow of argon and subsequently in vacuum.

step b) reaction with metallocene compound

A bright red solution of Cp_2TiCl_2 (20 μmol) in toluene (4 mL) was added to 200 mg of the above $\text{MgCl}_2/\text{Et}_n\text{Al}(\text{OEt})_{3-n}$ support and the mixture heated to 60 °C and kept at this (FE6163-EP)

temperature for 1 h, after which time a green solid was obtained, the liquid phase having become colourless. The liquid phase was removed by decantation and the solid was dried under a flow of argon at 60°C. The green colour of the immobilized catalyst was less intense than observed in the examples given in table 2.

step b) reaction with metallocene compound previously treated with TIBAL (AlⁱBu₃)

A bright red solution of Cp₂TiCl₂ (20 µmol) in toluene (4 mL) was mixed with AlⁱBu₃ (100 µmol), resulting in an immediate change of colour to give a violet solution. After 1 h at room temperature, this solution was added to 200 mg of the above MgCl₂/Et_nAl(OEt)_{3-n} support and the mixture heated to 60 °C and kept at this temperature for 1 h, after which time a light green solid was obtained. In contrast to the experiment carried out without the catalyst/ AlⁱBu₃ precontact, the liquid phase was not colourless but remained violet. After removal of the liquid phase by decantation and washing with heptane (2 mL) the solid was dried under a flow of argon at 60°C. The results of the polymerization runs are reported in table 3.

Polymerization, general procedures

Polymerization runs 1 – 12 in table 2 were carried out in a 200 mL Büchi reactor equipped with a hollow-shaft turbine stirrer. 100 mg of immobilized catalyst was charged to the reactor, followed by 100 mL of heptane containing 1 mmol triisobutylaluminium (TIBAL). The reactor contents were heated in 5 min. to 50 °C at an ethylene overpressure pressure of 1 bar, after which the monomer pressure was increased to 5 bar and kept constant for 45 min. The stirrer rate was approx. 1200 rpm. After venting the reactor, the polymer slurry was mixed with 20 mL ethanol containing 9 % HCl, followed by 200 mL 1M HCl_{aq}, and stirred for 20 min. The polymer was recovered by filtration, washed with water (3 x 200 mL) and ethanol (2 x 30 mL) and dried in vacuo overnight at 70 °C.

All other polymerization runs in tables 2 and 3 were carried out in a 1 L Premex autoclave equipped with a Vortex stirrer. Petroleum ether (40-70, 450 mL) was introduced via a cannula. The reactor contents were stirred and heated to 50 °C. Triisobutylaluminium (TIBAL, 1 mmol) in petroleum ether (40-70, 10 mL) was introduced via the catalyst injection system. An ethylene overpressure of 1 bar was applied and stirring continued for 5-10 min. A slurry of the immobilized catalyst (100 (FE6163-EP)

16

mg) in petroleum ether (40-70, 10 mL) was introduced through the catalyst injection system, which was then flushed with a further 50 mL petroleum ether (40-70). The ethylene pressure was increased to 10 bar and kept constant for 2 h at a polymerization temperature of 50 °C, the stirrer speed being ca. 1000 rpm. Polymerization was terminated by injection of 20 mL methanol. After venting the reactor, the polymer was isolated as described above.

The polymerization results are reported in tables 2 and 3.

Molecular weights and molecular weight distributions of the resulting polymers were determined by high temperature GPC (PL-GPC210) at 135 °C using 1,2,4-trichlorobenzene as solvent.

(FE6163-EP)

Table 1.

| Support | Starting material | organo-aluminium compound | solvent | Al/EtOH molar ratio |
|---------|-----------------------------|---------------------------------|---------|---------------------|
| A | MgCl ₂ .1.1 EtOH | AlEt ₃ | toluene | 2 |
| B | MgCl ₂ .1.1 EtOH | Al ⁱ Bu ₃ | hexane | 2 |
| C | MgCl ₂ .2.1 EtOH | AlEt ₃ | toluene | 2 |
| D | MgCl ₂ .2.1 EtOH | Al ⁱ Bu ₃ | hexane | 2 |
| E | MgCl ₂ .2.1 EtOH | AlEt ₂ Cl | toluene | 3 |
| F | MgCl ₂ .2.8 EtOH | AlEt ₃ | toluene | 2 |
| G | MgCl ₂ .2.8 EtOH | Al ⁱ Bu ₃ | hexane | 2 |
| H* | MgCl ₂ .2.37EtOH | AlEt ₃ | toluene | 2 |

*comparative (non dehalcolated)

table 1 continued

| Support | Al, wt.-% | OEt, wt.-% | | Surface area |
|---------|-----------|------------|---|-----------------------|
| A | 4.10 | 4.9 | MgCl ₂ .0.18AlEt _{2.28} (OEt) _{0.72} | 39 m ² /g |
| B | 2.81 | 3.1 | MgCl ₂ .0.12Al ⁱ Bu _{2.34} (OEt) _{0.66} | n.a. |
| C | 4.80 | 5.6 | MgCl ₂ .0.22AlEt _{2.31} (OEt) _{0.69} | 373 m ² /g |
| D | 2.92 | 3.8 | MgCl ₂ .0.13Al ⁱ Bu _{2.22} (OEt) _{0.78} | n.a. |
| E | 6.83 | 7.8 | MgCl ₂ .0.36AlEt _{1.31} Cl(OEt) _{0.69} | n.a. |
| F | 5.98 | 6.5 | MgCl ₂ .0.29AlEt _{2.35} (OEt) _{0.65} | n.a. |
| G | 4.14 | 4.6 | MgCl ₂ .0.21Al ⁱ Bu _{2.33} (OEt) _{0.67} | n.a. |
| H* | n.a. | n.a. | n.a. | n.a. |

* comparative (non dehalcolated magnesium alcohol adduct)

n.a. not available

18

table 2

| Run | Support | titanocene | loading on support | Activity | M _w | M _w /M n |
|-----|---------|--|--------------------------|------------------|----------------|------------------------|
| | | | μmol/g | kg/mol.b ar.h | | |
| 1 | A | Cp ₂ TiCl ₂ | 100 | 218 | 1181500 | 2.6 |
| 2 | B | Cp ₂ TiCl ₂ | 100 | 207 | 728600 | 2.5 |
| 3 | C | Cp ₂ TiCl ₂ | 100 | 327 | 1106000 | 2.7 |
| 4 | C | Cp ₂ TiCl ₂ | 100 | 315 | n.a. | n.a. |
| 5 | C | Cp ₂ TiCl ₂ | 100 | 320 | n.a. | n.a. |
| 6 | C | Me ₂ Si(Me ₄ Cp)(N ^t B u)TiCl ₂ | 100 | 217 | 1113500 | 2.5 |
| 7 | D | Cp ₂ TiCl ₂ | 100 | 268 | 1038500 | 2.0 |
| 8 | E | Cp ₂ TiCl ₂ | 100 | 50 | 440300 | 2.1 |
| 9 | F | Cp ₂ TiCl ₂ | 100 | 85 | 1000400 | 2.8 |
| 10 | G | Cp ₂ TiCl ₂ | 100 | 89 | 963600 | 2.6 |
| 11 | C | Cp ₂ ZrCl ₂ | 100 | 114 | 734700 | 2.4 |
| 12 | C | <i>rac</i> -Et(Ind) ₂ ZrCl ₂ | 100 | 5 | 645400 | 2.1 |
| 13 | C | Cp ₂ TiCl ₂ | 50 | 343 | n.a. | n.a. |
| 14 | C | Cp ₂ TiCl ₂ | 25 | 432 | n.a. | n.a. |
| 15 | C | Cp ₂ TiCl ₂ | 10 | 627 | n.a. | n.a. |
| 16 | C | Cp[1,3-(2',6'- Me ₂ C ₆ H ₃) ₂ (CH ₂ N) ₂ C=N]TiCl ₂ | 100 | 201 | n.a. | n.a. |

(FE6163-EP)

Table 2 - continued

| Run | Support | titanocene | loading support | on | Activity | M _w | M _w /M _n |
|-----|---------|--|--------------------|----|------------------|----------------|--------------------------------|
| | | | μmol/g | | kg/mol.b ar.h | | |
| 17 | C | Cp[1,3-(2',6'- Me ₂ C ₆ H ₃) ₂ (CH ₂ N) ₂ C=N]TiCl ₂ | 5 | | 1834 | n.a. | n.a. |
| 18 | C | Me ₂ Si(Me ₄ Cp)(N ^t B u)TiCl ₂ | 5 | | 465 | n.a. | n.a. |
| 19 | C | (^t Bu ₃ P=N)CpTiCl ₂ | 5 | | 1230 | n.a. | n.a. |
| 20 | A | Cp ₂ TiCl ₂ | 10 | | 606* | 619400 | 2.3 |
| 21 | A | CpTiCl ₃ | 10 | | 7510* | 1081500 | 2.2 |
| 22 | A | (^t BuCp)TiCl ₃ | 10 | | 7520* | 865400 | 2.4 |
| 23 | A | (C ₅ H ₄ CM ₂ Ph)TiCl ₃ | 10 | | 7940* | 503300 | 2.5 |

*polymerization time 1 hour

n.a. not available

table 3 comparative examples

| Run | Support | titanocene | loading on support | Activity |
|-----------------|---------|--|--------------------|-----------------------|
| | | | $\mu\text{mol/g}$ | kg/mol.bar.h |
| 3 | C | Cp_2TiCl_2 | 100 | 327 |
| 24 [§] | C | $\text{Cp}_2\text{TiCl}_2^+$ | 100 | 91 |
| 6 | C | $\text{Me}_2\text{Si}(\text{Me}_4\text{Cp})(\text{N}^t\text{Bu})\text{TiCl}_2$ | 100 | 217 |
| 25 [§] | C | $\text{Me}_2\text{Si}(\text{Me}_4\text{Cp})(\text{N}^t\text{Bu})\text{TiCl}_2^+$ | 100 | 183 |
| 16 | C | $\text{Cp}[1,3-(2',6'-\text{Me}_2\text{C}_6\text{H}_3)_2(\text{CH}_2\text{N})_2\text{C}\equiv\text{N}]\text{TiCl}_2$ | 100 | 201 |
| 26 [§] | C | $\text{Cp}[1,3-(2',6'-\text{Me}_2\text{C}_6\text{H}_3)_2(\text{CH}_2\text{N})_2\text{C}\equiv\text{N}]\text{TiCl}_2^+$ | 100 | 47 |
| 27 [§] | C | $\text{rac-Et}(\text{Ind})_2\text{ZrCl}_2$ | 100 | 8 |
| 28 [§] | C | $\text{rac-Et}(\text{Ind})_2\text{ZrCl}_2^+$ | 100 | 20 |
| 29 [§] | H | Cp_2TiCl_2 | 100 | 262 |
| 30 [§] | H | $\text{Cp}_2\text{TiCl}_2^+$ | 100 | 25 |

+precontacted with TIBA

§ comparative example

From the above table clearly results that the polymerization activity of the titanium-based catalyst system obtained according to the process of the present invention is higher than the activity of a similar catalyst system wherein the titanocene is pretreated with an organoaluminum compound such as TIBA. From the above table also results that this effect is achieved only when a titanium-based catalyst system is used, while for the zirconium-based catalyst the improvement of the activity due to the avoidance of the pretreatment with TIBA is not present (see entries 27 and 28). Moreover when a non dealcoholated magnesium chloride is used the activity of the titanocene-based catalyst results to be lower (see entries 29 and 30 in which the support H is used).

Claims

1. A catalyst system obtainable by the process comprising the following steps:

a) contacting:

- (i) a partially dealcoholated adduct of formula $MgT_2 \cdot wROH$ wherein T is chlorine, bromine, or iodine; R is a linear or branched C_1 - C_{10} alkyl radical, w ranges from 3 to 0.1, being also a non integer number; with
- (ii) an organo-aluminium compound of formula H_eAlU_{3-e} or $H_eAl_2U_{6-e}$, wherein the U substituents, same or different, are hydrogen atoms, halogen atoms, or hydrocarbon radicals containing from 1 to 20 carbon atoms optionally containing silicon or germanium atoms; with the proviso that at least one U is different from halogen, and e ranges from 0 to 1, being also a non-integer number;

to obtain an adduct of formula (I)



wherein

y ranges from 1.00 to 0.05;

Q has the same meaning of U excluding hydrogen and halogen atoms;

R has been described above

and J ranges from 0.01 to 3.00, being also a non-integer number.

- b) contacting the product obtained from step a) with at least one metallocene compound having titanium as central metal and at least one ligand having a cyclopentadienyl skeleton;

with the proviso that the metallocene compound of step b) is not previously treated with an organo-aluminium compound of formula H_eAlU_{3-e} or $H_eAl_2U_{6-e}$, or with an alumoxane.

- 2. The catalyst system according to claim 1 wherein in the partially dealcoholated adduct of formula $MgT_2 \cdot wROH$ T is chlorine; R is a linear C_1 - C_{10} alkyl radical; w ranges from 3 to 0.5.
- 3. The catalyst system according to claims 1 or 2 wherein in the organo-aluminium compound of formula H_eAlU_{3-e} or $H_eAl_2U_{6-e}$, U is a linear or branched C_1 - C_{20} -alkyl radical.

(FE6163-EP)


22

4. The catalyst system according to anyone of claims 1 to 3 wherein in the adduct of formula (I)




y ranges from 0.50 to 0.10; j ranges from 2.50 to 2.00.


5. The catalyst system according to any one of claims 1 to 4 wherein the adduct of formula (I) has a surface area (BET) higher than 30 m²/g.
6. The catalyst system according to anyone of claims 1 to 5 wherein the amount of titanocene compound supported on the adduct of formula (I) in step b) is generally between 1000 μmol/g of support and 1 μmol/g of support.
7. The catalyst system according to anyone of claims 1 to 6 wherein the titanocene compounds to be used in step b) belong to the following formulas (II), (III), (IV) or (V):




(II)



(III)



(IV)



(V)

wherein

Ti is titanium;

the substituents X, equal to or different from each other, are monoanionic sigma ligands selected from the group consisting of hydrogen, halogen, R⁶, OR⁶, OCOR⁶,

23

SR^6 , NR^6_2 and PR^6_2 , wherein R^6 is a hydrocarbon radical containing from 1 to 20 carbon atoms optionally containing one or more Si or Ge atoms;

p is an integer ranging from 1 to 2;

L is a divalent bridging group selected from C_1 - C_{20} alkylidene, C_3 - C_{20} cycloalkylidene, C_6 - C_{20} arylidene, C_7 - C_{20} alkylarylidene, or C_7 - C_{20} arylalkylidene radicals optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements, and silylidene radical containing up to 5 silicon atoms

R^1 , R^2 , R^3 , R^4 and R^5 , equal to or different from each other, are hydrogen atoms, C_1 - C_{40} hydrocarbon groups optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or two adjacent R^1 , R^2 , R^3 , R^4 and R^5 form one or more 3-7 membered ring optionally containing heteroatoms belonging to groups 13-17 of the periodic table;

A is a NR^8 , O , S radical, wherein R^8 is a C_1 - C_{20} hydrocarbon group optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

B is a hydrogen atom, a halogen atom, R^6 , OR^6 , $OCOR^6$, SR^6 , NR^6_2 and PR^6_2 , wherein R^6 has been described above; otherwise B is a NR^9 radical wherein R^9 is a C_1 - C_{40} hydrocarbon group optionally containing one or more heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

8. A process for (co)polymerizing olefins containing from 2 to 20 carbon atoms comprising contacting one or more of said olefins under polymerization conditions in the presence of the catalyst system of claims 1-7.
9. The process according to claim 8 wherein one or more alpha-olefins are (co)polymerized.
10. The process according to claim 9 wherein said alpha olefins are propylene, ethylene, 1-butene, 1-hexene and 1-octene.

24

Abstract

A catalyst system obtainable by the process comprising the steps of contacting an adduct of formula (I)



wherein T is chlorine, bromine, or iodine; R is a linear or branched C_1 - C_{10} alkyl radical; y ranges from 1.00 to 0.05; and j ranges from 0.01 to 3.00; with at least one metallocene compound having titanium as central metal and at least one ligand having a cyclopentadienyl skeleton.

(FE6163-EP)